

PURAFIL ENVIRONMENTAL CORROSION REPORT

27-May-2010

Company: 110287

Sales Order #: C002682
 CCC Panel #: P67436
 Date In: 05-May-2010
 Date Out: 20-May-2010
 Days In Service: 15

Room Area ID:
 Reference #:



| |
|--|
| CCC Panel # P67436 |
| ISA Class G1 Mild |
| Copper Corrosion 239 Å/30 Days |
| Silver Corrosion 660 Å/30 Days |

(see next page for complete analysis)

Summary for PURAFIL CCC # P67436

The electrolytic reduction analysis on Corrosion Classification Coupon #P67436 shows the presence of only very low concentrations of contaminants in the environment tested. The hydrogen sulfide level is not expected to exceed 3 ppb and the sulfur dioxide level should be less than 10 ppb. During the test period, corrosion, as shown by the copper coupon, is not a factor in determining equipment reliability.

Please note: Copper's reactivity is sensitive to temperature and relative humidity and can therefore exhibit seasonal variation. For example, below 30% relative humidity (typical for heated indoor air in winter), copper readings will be dramatically reduced. However, silver's reactivity is not affected by temperature and relative humidity. Due to the elevated level of film growth on the silver coupon, corrosion may be a factor in determining equipment reliability; continued monitoring is recommended.

Your local representative for additional information and assistance is:
 Environmental Health and Eng
 117 Fourth Avenue, Needham MA 02494, USA
 tminegishi@eheinc.com

Purafil, Inc. / 2654 Weaver Way, Doraville GA 30340 USA / (770) 662-8545 / (770) 263-6922
 Email: purafil@purafil.com / Internet: http://www.purafil.com

Displaying Page 1 [Display Page 2](#)

PURAFIL CCC # P67436 Analysis Results

| Corrosion Film Composition | | | | Gold Coupon - Magnified 20x |
|----------------------------|-------------|--------|---------|--------------------------------|
| | Projections | | | |
| | 30 Days | 1 Year | 5 Year | |
| Copper Films | | | | |
| Cu ₂ S | 0 Å | 0 Å | 0 Å | |
| Cu ₂ O | 239 Å | 323 Å | 422 Å | |
| Unknowns | 0 Å | 0 Å | 0 Å | |
| Totals | 239 Å | 323 Å | 422 Å | |
| Silver Films | | | | |
| AgCl | 0 Å | 0 Å | 0 Å | |
| Ag ₂ S | 617 Å | 7516 Å | 37580 Å | |
| Unknowns | 43 Å | 523 Å | 2614 Å | |
| Totals | 660 Å | 8039 Å | 40194 Å | |

Gold Pore Corrosion:
Note: 1000 Å = 0.1 micron

Equipment Reliability Correlation
(ISA Standard S71.04-1985 for Copper)

