

# PURAFIL ENVIRONMENTAL CORROSION REPORT

11-Jun-2010

Company: 110977

Sales Order #: C002697  
 CCC Panel #: P67947  
 Date In: 19-May-2010  
 Date Out: 02-Jun-2010  
 Days In Service: 14

Room Area ID:  
 Reference #:

**DO NOT TOUCH METAL COUPON**

**Corrosion Classification Coupon**

Company		110977	
Address			
Room/Area I.D.			
Date In	5/19/10	Time In:	a.m. 6 <sup>00</sup> p.m.
Date Out	6/2/10	Time Out:	a.m. 6 <sup>00</sup> p.m.
Coupon #	P67947	Tracking #	02697
Serial #			

Industrial   
 ERM   
 Preservation   
 CIF

**PURAFIL**  
 First...in clean air

2654 Weaver Way • Doraville, Georgia 30340  
 Ph: (770) 662-8545 • (800) 222-6367  
 Ex: (770) 263-6922 • www.purafil.com

**CCC Panel # P67947**

**ISA Class G1**  
 Mild

**Copper Corrosion**  
 295 Å/30 Days

**Silver Corrosion**  
 502 Å/30 Days

(see next page for complete analysis)

## Summary for PURAFIL CCC # P67947

The electrolytic reduction analysis on Corrosion Classification Coupon #P67947 shows the presence of only very low concentrations of contaminants in the environment tested. The hydrogen sulfide level is not expected to exceed 3 ppb and the sulfur dioxide level should be less than 10 ppb. During the test period, corrosion, as shown by the copper coupon, is not a factor in determining equipment reliability.

Please note: Copper's reactivity is sensitive to temperature and relative humidity and can therefore exhibit seasonal variation. For example, below 30% relative humidity (typical for heated indoor air in winter), copper readings will be dramatically reduced. However, silver's reactivity is not affected by temperature and relative humidity. Due to the elevated level of film growth on the silver coupon, corrosion may be a factor in determining equipment reliability; continued monitoring is recommended.

Your local representative for additional information and assistance is:  
 Environmental Health and Eng  
 117 Fourth Avenue, Needham MA 02494, USA  
 tminegishi@eheinc.com

---

Purafil, Inc. / 2654 Weaver Way, Doraville GA 30340 USA / (770) 662-8545 / (770) 263-6922  
 Email: purafil@purafil.com / Internet: http://www.purafil.com

---

Displaying Page 1    [Display Page 2](#)

**PURAFIL CCC # P67947 Analysis Results**

<b>Corrosion Film Composition</b>				<b>Gold Coupon - Magnified 20x</b>
	Projections			
	<u>30 Days</u>	<u>1 Year</u>	<u>5 Year</u>	
<b>Copper Films</b>				
Cu <sub>2</sub> S	0 Å	0 Å	0 Å	
Cu <sub>2</sub> O	236 Å	315 Å	412 Å	
Unknowns	59 Å	79 Å	104 Å	
Totals	295 Å	394 Å	516 Å	
<b>Silver Films</b>				
AgCl	0 Å	0 Å	0 Å	
Ag <sub>2</sub> S	421 Å	5124 Å	25622 Å	
Unknowns	81 Å	980 Å	4901 Å	
Totals	502 Å	6104 Å	30523 Å	

**Gold Pore Corrosion:**  
 Note: 1000 Å = 0.1 micron

**Equipment Reliability Correlation**  
 (ISA Standard S71.04-1985 for Copper)

