

PURAFIL ENVIRONMENTAL CORROSIONITY REPORT

29-Jun-2010

Company: 111337

Sales Order #: C002697
CCC Panel #: P67993
Date In: 04-Jun-2010
Date Out: 18-Jun-2010
Days In Service: 14

Room Area ID:
Reference #:



DO NOT TOUCH METAL COUPON

Corrosion Classification Coupon

Company		111337	
Address			
Room/Area I.D.			
Date In: 6/4/10	Time In: 1140 a.m.	p.m.	
Date Out: 6/18/10	Time Out: 1050 a.m.	p.m.	
Coupon #: 67993	Tracking #: C02697		
Serial #			

☐ Industrial ☐ ERM ☐ Preservation ☐ CIF

PURAFIL
First...in clean air

2654 Weaver Way • Doraville, Georgia 30340
Ph: (770) 662-8545 • (800) 222-6367
Fx: (770) 263-6922 • www.purafil.com

CCC Panel # P67993

ISA Class G1
Mild

Copper Corrosion
202 Å/30 Days

Silver Corrosion
401 Å/30 Days

(see next page for complete analysis)

Summary for PURAFIL CCC # P67993

The electrolytic reduction analysis on Corrosion Classification Coupon #P67993 shows the presence of only very low concentrations of contaminants in the environment tested. The hydrogen sulfide level is not expected to exceed 3 ppb and the sulfur dioxide level should be less than 10 ppb. During the test period, corrosion, as shown by the copper coupon, is not a factor in determining equipment reliability.

Please note: Copper's reactivity is sensitive to temperature and relative humidity and can therefore exhibit seasonal variation. For example, below 30% relative humidity (typical for heated indoor air in winter), copper readings will be dramatically reduced. However, silver's reactivity is not affected by temperature and relative humidity. Due to the elevated level of film growth on the silver coupon, corrosion may be a factor in determining equipment reliability; continued monitoring is recommended.

Your local representative for additional information and assistance is:
Environmental Health and Eng
117 Fourth Avenue, Needham MA 02494, USA
tminegishi@eheinc.com

Purafil, Inc. / 2654 Weaver Way, Doraville GA 30340 USA / (770) 662-8545 / (770) 263-6922
Email: purafil@purafil.com / Internet: http://www.purafil.com

PURAFIL CCC # P67993 Analysis Results

Corrosion Film Composition				Gold Coupon - Magnified 20x
	Projections			
	<u>30 Days</u>	<u>1 Year</u>	<u>5 Year</u>	
Copper Films				
Cu ₂ S	0 Å	0 Å	0 Å	
Cu ₂ O	202 Å	270 Å	353 Å	
Unknowns	0 Å	0 Å	0 Å	
Totals	202 Å	270 Å	353 Å	
Silver Films				
AgCl	0 Å	0 Å	0 Å	
Ag ₂ S	401 Å	4880 Å	24402 Å	
Unknowns	0 Å	0 Å	0 Å	
Totals	401 Å	4880 Å	24402 Å	
Gold Pore Corrosion:				
Note: 1000 Å = 0.1 micron				

Equipment Reliability Correlation
(ISA Standard S71.04-1985 for Copper)