

# PURAFIL ENVIRONMENTAL CORROSION REPORT

21-Oct-2010

Company: 116147

Sales Order #: C002697

CCC Panel #: P68018


Date In: 22-Sep-2010

Date Out: 06-Oct-2010

Days In Service: 14

Room Area ID:

Reference #:



**DO NOT TOUCH METAL COUPON**

**Corrosion Classification Coupon**

Company <b>116147</b>	
Address	
Room/Area I.D.	
Date In <b>9/22/10</b>	Time In: <b>1:50</b> p.m.
Date Out <b>10/6/10</b>	Time Out: <b>8:15</b> a.m.
Coupon # <b>68018</b>	Tracking # <b>02697</b>
Serial #	
<input type="checkbox"/> Industrial <input type="checkbox"/> ERM <input type="checkbox"/> Preservation <input type="checkbox"/> CIF	

**PURAFIL**  
First...in clean air

2654 Weaver Way • Doraville, Georgia 30340  
Ph: (770) 662-8545 • (800) 222-6367  
Fx: (770) 263-6922 • www.purafil.com

<b>CCC Panel # P68018</b>
<b>ISA Class G1</b>
Mild

<b>Copper Corrosion</b>
257 Å/30 Days
<b>Silver Corrosion</b>
220 Å/30 Days

(see next page for complete analysis)

### Summary for PURAFIL CCC # P68018

The electrolytic reduction analysis on Corrosion Classification Coupon #P68018 shows the presence of only very low concentrations of contaminants in the environment tested. The hydrogen sulfide level is not expected to exceed 3 ppb and the sulfur dioxide level should be less than 10 ppb. Corrosion is not a factor in determining equipment reliability in this environment.

Your local representative for additional information and assistance is:

Environmental Health and Eng  
117 Fourth Avenue, Needham MA 02494, USA  
tminegishi@eheinc.com

---

Purafil, Inc. / 2654 Weaver Way, Doraville GA 30340 USA / (770) 662-8545 / (770) 263-6922  
Email: purafil@purafil.com / Internet: http://www.purafil.com

---

Displaying Page 1

[Display Page 2](#)

**PURAFIL CCC # P68018 Analysis Results**

<b>Corrosion Film Composition</b>				<b>Gold Coupon - Magnified 20x</b>
	Projections			
	<u>30 Days</u>	<u>1 Year</u>	<u>5 Year</u>	
<b>Copper Films</b>				
Cu <sub>2</sub> S	0 Å	0 Å	0 Å	
Cu <sub>2</sub> O	257 Å	343 Å	449 Å	
Unknowns	0 Å	0 Å	0 Å	
Totals	257 Å	343 Å	449 Å	
<b>Silver Films</b>				
AgCl	0 Å	0 Å	0 Å	
Ag <sub>2</sub> S	220 Å	2684 Å	13421 Å	
Unknowns	0 Å	0 Å	0 Å	
Totals	220 Å	2684 Å	13421 Å	

**Gold Pore Corrosion:**  
 Note: 1000 Å = 0.1 micron

**Equipment Reliability Correlation**  
 (ISA Standard S71.04-1985 for Copper)

